



Sinvicomp SBF5758

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Food Contact Acceptable
Uses	• Shrink Wrap
Forms	• Pellets
Processing Method	• Blow Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.32		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/21.6 kg)	54	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5690	psi	ASTM D638
Tensile Elongation (Break)	190	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.8	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	171	°F	ASTM D1525

Notes

¹ Typical properties: these are not to be construed as specifications.