



Sinvicomp SBB3700

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Food Contact Acceptable • Medium Impact Resistance
Uses	• Bottles • Containers
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Blow Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	7040	psi	ASTM D638
Tensile Elongation ² (Break)	150	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.5	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	79		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	181	°F	ASTM D1525

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min