



Sinvicomp SFR5800C2

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Features	• Foamable		
Uses	• Foam	• Profiles	
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	31900	psi	ISO 178
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	167	°F	ASTM D1525
Thermal Stability ² (356°F)	> 1	hr	ASTM D2115-92

Notes

¹ Typical properties: these are not to be construed as specifications.

² Congo Red