



Sinvicomp SIF5166

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• High Stiffness
Uses	• Wire & Cable Applications
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.56		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	2470	psi	ASTM D638
Tensile Elongation ² (Break)	190	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	91		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Thermal Stability ³ (374°F)	> 1	hr	BS 2782
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength (176°F, 168 hr)	10	%	ASTM D638
Change in Ultimate Elongation (176°F, 168 hr)	15	%	ASTM D638
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (68°F)	1.0E+14	ohms·cm	BS 2782

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min

³ Congo Red