



Sinvicomp SIC3707J

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

Product Description

"Sinvicomp" SIC 3707J is an extrusion grade polyvinylchloride compound available in pellet granular form. SIC 3707J provides high impact performance suitable for integrated circuit (IC) tubes.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific	
Features	• High Impact Resistance	
Uses	• Rigid Packaging	• Tubing
Forms	• Pellets	
Processing Method	• Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	7250	psi	ASTM D638
Tensile Elongation ² (Break)	160	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.2	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	81		ASTM D2240

Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160oC to 180oC. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone 160°C

Compression zone 160°C ~ 170°C

Mixing zone 170°C ~ 180°C

Nozzle / Die zone 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min