



Sinvicomp SIZ5065

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

Product Description

"Sinvicomp" SIZ 5065 is a wire & cable polyvinylchloride compound available in pellet form. SIZ 5065 provides good performance for insulation of electrical wires.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• High Stiffness
Uses	• Insulation
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.32		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	2760	psi	ASTM D638
Tensile Elongation (Break)	320	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	38		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863

Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160°C to 185°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C
Compression zone: 160°C~170°C
Mixing zone: 170°C~180°C
Nozzle/Die Zone: 185°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² @ 23°C