



Sinvicomp SRP3613A

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Good Impact Resistance
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.49 to 1.53		ASTM D638
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6530	psi	ASTM D638
Tensile Elongation (Break)	130	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.92	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	189	°F	ASTM D1525

Notes

¹ Typical properties: these are not to be construed as specifications.