



Sinvicomp SSZ4609S

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

Product Description

"Sinvicomp"SSZ 4609S is a wire & cable polyvinylchloride compound available in pellet form. SSZ 4609S provides good performance for jacketing of cables.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Uses	• Wire Jacketing
Wire Types (IEC 60502)	• ST1 • ST2
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.49		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	2320	psi	IEC 60811-1-1
Tensile Elongation (Break)	250	%	IEC 60811-1-1
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	91		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-0.400	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Mechanical Properties After Aging in Air Oven, 212°F, 168 hr ²			IEC 811-1-2
Change in Tensile Elongation	15	%	
Change in Tensile Strength	5	%	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (68°F)	1.0E+13	ohms·cm	BS 2782
Additional Information	Nominal Value	Unit	Test Method
Loss of Mass - 7 days, 100±2°C ³ (212°F)	1.20	mg/cm ²	IEC 811-3-2

Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C
Compression zone: 160°C~170°C
Mixing zone: 170°C~180°C
Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 100±2°C

³ 7 days, 100±2°C