



Sinvicomp SSF4265UV

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Flame Retardant • High Heat Resistance
Uses	• Appliance Wire Jacketing
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.53		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	2610	psi	ASTM D638
Tensile Elongation ² (Break)	200	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	93		ASTM D2240
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength (277°F, 168 hr)	10	%	ASTM D638
Change in Ultimate Elongation (277°F, 168 hr)	15	%	ASTM D638

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min