



Sinvicomp SSN6028A

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Abrasion Resistant • Chemical Resistant
Uses	• Wire & Cable Applications
Wire Types	• 5V-90
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	2900	psi	IEC 811-1-1
Tensile Elongation ² (Break)	380	%	IEC 811-1-1
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ASTM D2240
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength (239°F, 504 hr)	25	%	AS 3147/3191
Change in Ultimate Elongation (239°F, 504 hr)	35	%	AS 3147/3191

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min