



Sinvicomp TAZ57038CR

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

Product Description

"Sinvicomp" TAZ57038CR is a wire & cable polyvinylchloride compound available in pellet form. TAZ57038CR provides good performance for jacketing of cables.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Uses	• Communication Cable Jacketing • Flame Retardant Jacketing
Wire Types (UL 444)	• CAT-6 • CMR
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.56		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	2610	psi	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	51		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	3.20	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Mechanical Properties After Aging in Air Oven, 212°F, 240 hr			ASTM D638
Change in Tensile Elongation	20	%	
Change in Tensile Strength	10	%	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	42	%	ASTM D2863

Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160°C to 185°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C

Compression zone: 160°C~170°C

Mixing zone: 175°C~185°C

Nozzle/Die Zone: 180°C~185°C

Notes

¹ Typical properties: these are not to be construed as specifications.