



Sinvicomp SRT5713

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Uses	• Electrical Parts • Fittings
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6670	psi	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	9.4	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	176	°F	ASTM D1525

Notes

¹ Typical properties: these are not to be construed as specifications.