+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



Vital-Line SHE5600A

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information				
Product Description				
Vital-Line SHE 5600A is a Poly	vinyl Chloride Medical Extrusion Compound available in pellet form.			
General				
Material Status	Commercial: Active			
Availability	Asia Pacific			
Features	DEHP Plasticizer Ethylene Oxide Sterilizable			
Uses	Medical/Healthcare Applications			
Forms	• Pellets			
Processing Method	Extrusion			

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.21		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength ²	2610	psi	ASTM D638	
Tensile Elongation ² (Break)	390	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	72		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Heat Stability	> 30.0	min	ASTM D2115-92	
Additional Information				

Typical temperature profile for processing compound is from 140oC to 170oC. The optimum temperatures depend on the type of machine as well as screw design being used to process.

Feeding zone 140°C Compression zone 145°C ~ 155°C Mixing zone 150°C ~ 165°C Nozzle / Die zone 160°C ~ 170°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 20 in/min