



APEX® 90-P513A-80-NT

Teknor Apex Company - Polyvinyl Chloride + PUR

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Medical/Healthcare Applications		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.22		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2800	psi	ASTM D638
Tensile Elongation (Break)	490	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	80		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	140	°F	ASTM D794
Brittleness Temperature	-49.0	°F	ASTM D746

Notes

¹ Typical properties: these are not to be construed as specifications.