



# Medalist® MD-10108 AP NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

Medalist MD-10108 AP is a high performance thermoplastic elastomer specifically designed for medical and healthcare applications. Medalist MD-10108 AP is a low hardness, low density, lubricated grade that can be sterilized and is suitable for injection molding.

### General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Ethylene Oxide Sterilizable • Good Colorability • Good Flexibility • Good Moldability • Good Sterilizability	• Good Toughness • Halogen Free • High Flow • Low Density • Low Hardness • Lubricated	• Radiation Sterilizable • Resilient • Slip • Without Fillers
Uses	• Dental Applications • Disposable Hospital Goods • Handles • Knobs	• Medical Devices • Medical/Healthcare Applications • Overmolding • Pharmaceuticals	• Rubber Replacement • Soft Touch Applications
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.850		ASTM D792
Melt Mass-Flow Rate (MFR) (150°C/2.16 kg)	6.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (50% Strain)	21.8	psi	ASTM D412
Tensile Stress <sup>2</sup> (100% Strain)	33.4	psi	ASTM D412
Tensile Stress <sup>2</sup> (300% Strain)	58.0	psi	ASTM D412
Tensile Strength <sup>2</sup> (Break)	743	psi	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	1300	%	ASTM D412
Tear Strength <sup>2</sup>	80.0	lbf/in	ASTM D624
Compression Set <sup>3</sup> (73°F, 22 hr)	8.0	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	10		
Shore A, 5 sec, Injection Molded	8		

## Medalist® MD-10108 AP NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	300 to 320	°F
Middle Temperature	320 to 350	°F
Front Temperature	350 to 375	°F
Nozzle Temperature	330 to 375	°F
Processing (Melt) Temp	330 to 375	°F
Mold Temperature	60 to 100	°F
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 100	psi
Cushion	0.150 to 0.500	in

### Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C, 20 in/min

<sup>3</sup> Type 1