



Elexar® EL-8732R

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Elexar EL-8732R is a high performance, flame retardant thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Elexar EL-8732R is a medium hardness grade. This grade is UL listed and is suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant • General Purpose • Good Colorability • Good Flexibility • Good Weather Resistance • Halogenated	• Heat Aging Resistant • High Elasticity • High Elongation • High Hardness • High Specific Gravity • High Tensile Strength	• Medium Flow • Ozone Resistant • Sunlight Resistant (720 hours) • UV Resistant
Uses	• Appliance Wire Insulation • Appliance Wire Jacketing • Cable Jacketing • Connectors	• Flexible Cord Jacketing • Industrial Cable Insulation • Terminal Cable Jacketing • Underground Power Cable	• Wire & Cable Applications • Wire Jacketing
Agency Ratings	• UL 1581		
UL File Number	• QMTT2.E73402		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18		ASTM D792
Melt Mass-Flow Rate (MFR)	10	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ^{2, 3} (100% Strain, 0.0200 in)	470	psi	ASTM D412
Tensile Stress ^{2, 3} (300% Strain, 0.0200 in)	690	psi	ASTM D412
Tensile Strength ^{2, 3} (Yield, 0.0200 in)	1800	psi	ASTM D412
Tensile Elongation ^{2, 3} (Break, 0.0200 in)	650	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	81		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	UL 1581
Brittleness Temperature	-76.0	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (277°F, 168 hr)	-10	%	ASTM D573
Change in Ultimate Elongation in Air (277°F, 168 hr)	-7.0	%	ASTM D573
Change in Tensile Strength 140°F, 168 hr, in IRM 902 Oil	-4.0	%	ASTM D471
Change in Ultimate Elongation 140°F, 168 hr, in IRM 902 Oil	2.0	%	ASTM D471

Ellexar® EL-8732R

Teknor Apex Company - Thermoplastic Elastomer

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
73°F	1.4E+16	ohms·cm	
122°F	6.5E+14	ohms·cm	
Dielectric Strength	640	V/mil	ASTM D149
Dielectric Constant (1 kHz)	2.40		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.12 in, All Colors)	V-2		UL 94
Oxygen Index	23	%	ASTM D2863

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	390 to 420	°F
Middle Temperature	415 to 430	°F
Front Temperature	430 to 440	°F
Nozzle Temperature	430 to 445	°F
Processing (Melt) Temp	430 to 445	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 410	°F
Cylinder Zone 2 Temp.	390 to 420	°F
Cylinder Zone 3 Temp.	415 to 430	°F
Cylinder Zone 4 Temp.	430 to 445	°F
Cylinder Zone 5 Temp.	430 to 440	°F
Die Temperature	430 to 445	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ die cut from extruded tapes