



Medalist® MD-14165 AP NAT XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

The Medalist MD-14100 series are high performance thermoplastic elastomers designed for medical and healthcare applications requiring high elasticity and excellent moldability. Medalist MD-14165 AP NAT XRD1 is a medium hardness, high density, opaque grade, available in NAT and colors, which can be sterilized and exhibits excellent adhesion to polypropylene.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Autoclave Sterilizable • Chemical Resistant • Ethylene Oxide Sterilizable • Good Adhesion • Good Moldability	• Good Sterilizability • Good Toughness • Halogen Free • High Density • Lubricated	• Medium Flow • Medium Hardness • Radiation Sterilizable
Uses	• Bushings • Closures • Disposable Hospital Goods • Flexible Grips	• Grommets • Knobs • Medical/Healthcare Applications • Pharmaceuticals	• Plugs • Rubber Replacement
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	435	psi	ASTM D412
Tensile Stress ² (300% Strain)	580	psi	ASTM D412
Tensile Strength ² (Break)	1020	psi	ASTM D412
Tensile Elongation ² (Break)	550	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	68		
Shore A, 5 sec	66		

Medalist® MD-14165 AP NAT XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	320 to 350	°F
Middle Temperature	360 to 400	°F
Front Temperature	380 to 420	°F
Nozzle Temperature	360 to 440	°F
Processing (Melt) Temp	360 to 440	°F
Mold Temperature	80 to 120	°F
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 0.500	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

For applications where adhesion or overmolding to polypropylene (PP) is required, a higher processing temperature (up to 480 °F) is recommended.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min