



Medalist® MD-16110 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Medalist MD-16110 is a high performance thermoplastic elastomer specifically designed for healthcare and medical applications. Medalist MD-16110 is a low hardness, low density, lubricated grade that can be sterilized and is suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Ethylene Oxide Sterilizable • Good Colorability • Good Flexibility • Good Moldability • Good Sterilizability	• Good Toughness • Halogen Free • High Flow • Low Density • Low Hardness • Low Specific Gravity	• Lubricated • Resilient • Slip • Without Fillers
Uses	• Dental Applications • Disposable Hospital Goods • Handles	• Knobs • Medical/Healthcare Applications • Overmolding	• Pharmaceuticals • Rubber Replacement • Soft Touch Applications
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.860		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	21	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (50% Strain)	21.8	psi	ASTM D412
Tensile Stress ² (100% Strain)	29.0	psi	ASTM D412
Tensile Stress ² (300% Strain)	49.3	psi	ASTM D412
Tensile Strength ² (Break)	748	psi	ASTM D412
Tensile Elongation ² (Break)	1300	%	ASTM D412
Tear Strength ²	100	lbf/in	ASTM D624
Compression Set ³ (73°F, 22 hr)	13	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	11		
Shore A, 5 sec, Injection Molded	9		

Medalist® MD-16110 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	285 to 320	°F
Middle Temperature	305 to 340	°F
Front Temperature	340 to 375	°F
Nozzle Temperature	330 to 375	°F
Processing (Melt) Temp	330 to 375	°F
Mold Temperature	60 to 100	°F
Injection Rate	Slow-Moderate	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 0.500	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1