



Medalist® MD-34040 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Medalist MD-34040 is a high performance thermoplastic elastomer specifically designed for overmolding and multi-shot molding applications in the healthcare/medical segment. Medalist MD-34040 is a medium hardness, medium density, halogen-free grade that bonds to ABS, PC/ABS, and PC.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant • Bondability • Chemical Resistant • Ethylene Oxide Sterilizable • Filled • Good Colorability	• Good Flexibility • Good Flow • Good Impact Resistance • Good Moldability • Good Scratch Resistance • Good Sterilizability	• Halogen Free • Lubricated • Medium Density • Medium Hardness • Radiation Sterilizable • Steam Sterilizable
Uses	• Bonding • Medical/Healthcare Applications	• Overmolding • Soft Touch Applications	
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.06		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	33	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	185	psi	ASTM D412
Tensile Stress ² (300% Strain)	375	psi	ASTM D412
Tensile Strength ² (Break)	1110	psi	ASTM D412
Tensile Elongation ² (Break)	650	%	ASTM D412
Tear Strength ²	177	lbf/in	ASTM D624
Compression Set ³			ASTM D395B
73°F, 22 hr	40	%	
158°F, 22 hr	110	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	43		
Shore A, 5 sec, Injection Molded	40		
Additional Information	Nominal Value	Unit	
Adhesion to ABS	16	lbf/in	
Adhesion to PC	13	lbf/in	
Adhesion to PC/ABS	23	lbf/in	

Medalist® MD-34040 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	320 to 360	°F
Middle Temperature	340 to 380	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	360 to 390	°F
Processing (Melt) Temp	360 to 400	°F
Mold Temperature	60 to 100	°F
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1