



Medalist® MD-47235 XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Medalist MD-47235 XRD1 is designed for medical and healthcare applications requiring high elasticity and excellent melt strength. Medalist MD-47235 XRD1 is a low hardness, low density, high performance thermoplastic elastomer, available in NAT and colors, which can be sterilized, exhibits excellent adhesion to polypropylene and is suited for extrusion and injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Autoclave Sterilizable • Chemical Resistant • Ethylene Oxide Sterilizable • Good Adhesion • Good Melt Strength • Good Moldability	• Good Sterilizability • Good Toughness • Halogen Free • Low Density • Low Flow • Low Hardness	• Low Specific Gravity • Lubricated • Radiation Sterilizable • Resilient • Without Fillers
Uses	• Bushings • Closures • Disposable Hospital Goods • Flexible Grips	• Grommets • Knobs • Medical/Healthcare Applications • Pharmaceuticals	• Plugs • Rubber Replacement
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.892		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (50% Strain)	100	psi	ASTM D412
Tensile Stress ² (100% Strain)	120	psi	ASTM D412
Tensile Stress (300% Strain)	220	psi	ASTM D412
Tensile Strength ² (Break)	1000	psi	ASTM D412
Tensile Elongation ² (Break)	800	%	ASTM D412
Tear Strength ²	115	lbf/in	ASTM D624
Compression Set			ASTM D395
73°F, 22 hr ³	19	%	
158°F, 22 hr	37	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	38		
Shore A, 5 sec	35		

Medalist® MD-47235 XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	320 to 491	°F
Middle Temperature	360 to 491	°F
Front Temperature	380 to 491	°F
Nozzle Temperature	360 to 491	°F
Processing (Melt) Temp	360 to 491	°F
Mold Temperature	80 to 140	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 150	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 0.500	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	340 to 370	°F
Cylinder Zone 2 Temp.	360 to 385	°F
Cylinder Zone 3 Temp.	365 to 400	°F
Cylinder Zone 4 Temp.	380 to 420	°F
Cylinder Zone 5 Temp.	400 to 440	°F
Die Temperature	400 to 440	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Screen Pack Recommendation: 60/200/200/60 to 60/200/400/400/200/60 mesh size

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1