



Medalist® MD-466A GREEN

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Medalist MD-466A GREEN is a high performance thermoplastic elastomer specifically designed for healthcare and medical applications. Medalist MD-466A GREEN is a medium hardness, low density, RoHS compliant grade suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Moldability • Low Density	• Low Flow • Lubricated	• Medium Hardness • Without Fillers
Uses	• Medical/Healthcare Applications • Pharmaceuticals		• Safety Equipment
RoHS Compliance	• RoHS Compliant		
Appearance	• Green		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.892		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	400	psi	ASTM D412
Tensile Strength (Break)	1200	psi	ASTM D412
Tensile Elongation (Break)	750	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	47		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	260 to 300	°F
Middle Temperature	280 to 320	°F
Front Temperature	300 to 340	°F
Nozzle Temperature	340 to 380	°F
Processing (Melt) Temp	340 to 380	°F
Mold Temperature	70 to 100	°F
Injection Pressure	200 to 800	psi
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Medalist® MD-466A GREEN

Teknor Apex Company - Thermoplastic Elastomer

Injection Notes		
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).		
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	280 to 300	°F
Cylinder Zone 2 Temp.	300 to 320	°F
Cylinder Zone 3 Temp.	320 to 360	°F
Cylinder Zone 5 Temp.	340 to 380	°F
Die Temperature	360 to 400	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		

Notes

¹ Typical properties: these are not to be construed as specifications.