



Monprene® CP-13258 NAT XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-13258 NAT XRD1 is a general purpose thermoplastic elastomer designed for a variety of consumer product applications, including toys, requiring a soft, rubber-like feel. Monprene CP-13258 NAT XRD1 is a low hardness, low density grade that is suitable for injection molding and is available in other colors.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Flow • Low Density	• Low Hardness • Low Specific Gravity	
Uses	• Consumer Applications • Flexible Grips	• General Purpose • Industrial Applications	• Rubber Replacement • Toys
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.932		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	18	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	551	psi	ASTM D412
Tensile Strength (Break)	1800	psi	ASTM D412
Tensile Elongation (Break)	1000	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	57		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi

Monprene® CP-13258 NAT XRD1 (PRELIMINARY DATA)
Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Notes

¹ Typical properties: these are not to be construed as specifications.