



Monprene® CP-13029 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-13029 is a high performance thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-13029 is a low density, low hardness, RoHS compliant grade that is suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Contact Clarity • General Purpose • Good Colorability • Good Flexibility	• Good Mold Release • Good Moldability • Halogen Free • High Elasticity	• High Elongation • Low Density • Low Hardness • Soft
Uses	• Consumer Applications • Gaskets	• General Purpose • Handles	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Translucent
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	12	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	130	psi	ASTM D412
Tensile Stress (300% Strain)	225	psi	ASTM D412
Tensile Strength (Break)	820	psi	ASTM D412
Tensile Elongation (Break)	780	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	32		
Shore A, 5 sec	30		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 400	°F
Middle Temperature	360 to 400	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	360 to 400	°F
Processing (Melt) Temp	360 to 400	°F

Monprene® CP-13029 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.