



Monprene® CP-15118 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-15118 is a high performance thermoplastic elastomer specifically designed for consumer and Industrial applications. Monprene CP-15118 is a low hardness, low density, RoHS compliant grade suitable for injection molding and extrusion applications.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Colorability • Good Flexibility • Good Moldability • Good Toughness	• Halogen Free • High Flow • Low Density • Low Hardness • Low Specific Gravity	• Lubricated • Resilient • Slip • Without Fillers
Uses	• Consumer Applications • Handles • Industrial Applications	• Knobs • Medical Devices • Overmolding	• Rubber Replacement • Soft Touch Applications • Soft Touch Grips
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.862		ASTM D792
Melt Mass-Flow Rate (MFR) (150°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (50% Strain)	47.9	psi	ASTM D412
Tensile Stress ² (100% Strain)	66.7	psi	ASTM D412
Tensile Stress ² (300% Strain)	115	psi	ASTM D412
Tensile Strength ² (Break)	892	psi	ASTM D412
Tensile Elongation ² (Break)	1200	%	ASTM D412
Tear Strength ²	100	lbf/in	ASTM D624
Compression Set ³ (73°F, 22 hr)	13	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	20		
Shore A, 5 sec, Injection Molded	18		

Monprene® CP-15118 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	300 to 320	°F
Middle Temperature	320 to 350	°F
Front Temperature	350 to 375	°F
Nozzle Temperature	330 to 375	°F
Processing (Melt) Temp	330 to 375	°F
Mold Temperature	60 to 100	°F
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 100	psi
Cushion	0.150 to 0.500	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	300 to 320	°F
Cylinder Zone 2 Temp.	320 to 350	°F
Cylinder Zone 3 Temp.	320 to 350	°F
Cylinder Zone 4 Temp.	340 to 360	°F
Cylinder Zone 5 Temp.	340 to 370	°F
Adapter Temperature	340 to 370	°F
Melt Temperature	340 to 370	°F
Die Temperature	340 to 370	°F

Extrusion Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

40/100/100/40 screen pack recommended for processing.

Screw Speed: 30 to 100 rpm recommended

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1