



Monprene® CP-17270

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

The Monprene CP-17200 Filled, High Flow Series of thermoplastic elastomer compounds, with good UV resistance, available in NAT or colors, from 40 to 80 Shore A, are designed specifically for EU consumer product applications requiring a soft, rubber-like feel. Monprene CP-17270 is a medium hardness, medium density grade that is suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Colorability	• Good Flexibility • Good Flow • Good Moldability • Lubricated	• Medium Density • Medium Hardness • UV Resistant
Uses	• Bushings • Consumer Applications • Flexible Grips • Gaskets	• Grommets • Handles • Luggage • Overmolding	• Plugs • Rubber Replacement • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.04		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	276	psi	ASTM D412
Tensile Stress (300% Strain)	377	psi	ASTM D412
Tensile Strength (Break)	1100	psi	ASTM D412
Tensile Elongation (Break)	800	%	ASTM D412
Compression Set			ASTM D395
73°F, 22 hr	31	%	
158°F, 22 hr	55	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	72		
Shore A, 5 sec	70		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	107	Pa·s	ASTM D3835

Monprene® CP-17270

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	95 to 120	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 4 Temp.	390 to 480	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.