



Monprene® CP-17280 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

The Monprene CP-17200 Filled, High Flow Series of thermoplastic elastomer compounds, with good UV resistance, available in NAT or colors, from 40 to 80 Shore A, are designed specifically for EU consumer product applications requiring a soft, rubber-like feel. Monprene CP-17280 is a medium hardness, medium density grade that is suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Colorability	• Good Flexibility • Good Flow • Good Moldability • Lubricated	• Medium Density • Medium Hardness • UV Resistant
Uses	• Bushings • Consumer Applications • Flexible Grips • Gaskets	• Grommets • Handles • Luggage • Overmolding	• Plugs • Rubber Replacement • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	479	psi	ISO 37
Tensile Stress (300% Strain)	595	psi	ISO 37
Tensile Strength (Break)	1090	psi	ISO 37
Tensile Elongation (Break)	600	%	ISO 37
Compression Set ²			ISO 815
73°F, 22 hr	36	%	
158°F, 22 hr	62	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	80		ISO 868
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	113	Pa·s	ISO 11443

Monprene® CP-17280 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	248 to 320	°F
Middle Temperature	320 to 446	°F
Front Temperature	356 to 446	°F
Nozzle Temperature	356 to 446	°F
Processing (Melt) Temp	356 to 446	°F
Mold Temperature	59 to 122	°F
Injection Rate	Fast	
Back Pressure	72.5 to 218	psi
Screw Speed	50 to 100	rpm
Cushion	0.118 to 0.787	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method B