



Monprene® CP-18160

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-18160 is a high performance thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-18160 is a medium hardness grade suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose • Good Colorability • Good Moldability • High Elongation	• High Flow • Low Density • Low Specific Gravity • Medium Hardness	• Slip • Without Fillers
Uses	• Consumer Applications • Gaskets	• Handles • Kitchenware	
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	435	psi	ASTM D412
Tensile Stress (300% Strain)	551	psi	ASTM D412
Tensile Strength (Break)	1400	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Tear Strength	190	lbf/in	ASTM D624
Compression Set (73°F, 22 hr)	18	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	62		
Shore A, 5 sec	60		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F

Monprene® CP-18160

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.