



Monprene® CP-18150 CLR XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-18150 CLR XRD1 is a high performance thermoplastic elastomer designed for a variety of industrial and consumer product applications requiring a soft, rubber-like feel. Monprene CP-18150 CLR XRD1 is a low hardness, low density, RoHS compliant grade suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Contact Clarity • Good Mold Release • Good Moldability • Good Processability	• High Elasticity • High Flow • Low Density • Low Specific Gravity	• Lubricated • Medium Hardness • Slip • Without Fillers
Uses	• Consumer Applications • Gaskets	• General Purpose • Handles	
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.882		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	34	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	870	psi	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 1 sec, Injection Molded)	50		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	

Monprene® CP-18150 CLR XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.