



Monprene® CP-18113 CLR

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-18113 CLR is a clear thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-18113 CLR is a low hardness, low density, Halogen free grade suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Colorability • Good Flexibility • Good Moldability • Good Processability	• Halogen Free • High Elongation • High Flow • Low Density	• Low Hardness • Resilient
Uses	• Consumer Applications • Flexible Grips • General Purpose	• Handles • Knobs • Rubber Replacement	• Soft Touch Applications • Sporting Goods
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.882		ASTM D792
Melt Mass-Flow Rate (MFR) (150°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	120	psi	ASTM D412
Tensile Stress ² (300% Strain)	205	psi	ASTM D412
Tensile Strength ² (Break)	650	psi	ASTM D412
Tensile Elongation ² (Break)	740	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	12		
Shore A, 5 sec	10		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 365	°F
Middle Temperature	360 to 390	°F
Front Temperature	390 to 420	°F

Monprene® CP-18113 CLR

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Nozzle Temperature	390 to 420	°F
Processing (Melt) Temp	390 to 420	°F
Mold Temperature	80 to 120	°F
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min