



Monprene® CP-29048 CLR

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-29048 CLR is a general purpose thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-29048 CLR is a transparent grade suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Good Clarity • Good Colorability • Good Mold Release	• Good Moldability • Good Processability • Low Density • Low Specific Gravity	• Medium Flow • Medium Hardness • Slip
Uses	• Consumer Applications • Gaskets	• Handles • Knobs	• Sporting Goods • Tubing
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.900		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	170	psi	
Flow : 100% Strain	299	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	365	psi	
Flow : 300% Strain	542	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1710	psi	
Flow : Break	1330	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	630	%	
Flow : Break	660	%	
Tear Strength ²			ASTM D624
Across Flow	238	lbf/in	
Flow	212	lbf/in	
Compression Set ³ (73°F, 22 hr)	16	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	50		
Shore A, 5 sec, Injection Molded	48		

Monprene® CP-29048 CLR

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	380 to 420	°F
Middle Temperature	380 to 420	°F
Front Temperature	380 to 420	°F
Nozzle Temperature	380 to 420	°F
Processing (Melt) Temp	380 to 420	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 400	°F
Cylinder Zone 2 Temp.	360 to 400	°F
Cylinder Zone 3 Temp.	360 to 400	°F
Cylinder Zone 4 Temp.	360 to 400	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	360 to 400	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1