



Monprene® CP-28150

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-28150 is a general purpose thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-28150 is a clear, medium hardness grade, suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Contact Clarity • Good Colorability • Good Mold Release • Good Moldability	• Good Processability • Low Density • Low Flow • Low Specific Gravity • Lubricated	• Medium Hardness • Slip • Without Fillers
Uses	• Consumer Applications • Film	• Gaskets • Tubing	• Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	241	psi	
Flow : 100% Strain	337	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	361	psi	
Flow : 300% Strain	474	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1680	psi	
Flow : Break	844	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	780	%	
Flow : Break	610	%	
Tear Strength ²			ASTM D624
Across Flow	187	lbf/in	
Flow	156	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	21	%	
158°F, 22 hr	43	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	53		
Shore A, 5 sec, Injection Molded	51		

Monprene® CP-28150

Teknor Apex Company - Thermoplastic Elastomer

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	420 to 460	°F
Middle Temperature	420 to 460	°F
Front Temperature	420 to 460	°F
Nozzle Temperature	420 to 460	°F
Processing (Melt) Temp	420 to 460	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Injection Notes		
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).		
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	400 to 440	°F
Cylinder Zone 2 Temp.	400 to 440	°F
Cylinder Zone 3 Temp.	400 to 440	°F
Cylinder Zone 4 Temp.	400 to 440	°F
Cylinder Zone 5 Temp.	400 to 440	°F
Die Temperature	400 to 440	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		
Notes		
¹ Typical properties: these are not to be construed as specifications.		
² Die C, 20 in/min		
³ Type 1		