



Monprene® CP-29043

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-29043 is a high performance thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-29043 is a medium hardness, low density, filled grade that is suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • Good Colorability • Good Mold Release	• Good Moldability • Good Processability • Low Density • Low Specific Gravity	• Lubricated • Medium Flow • Medium Hardness • Slip
Uses	• Consumer Applications • General Purpose	• Handles • Tubing	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.940		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	176	psi	
Flow : 100% Strain	261	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	414	psi	
Flow : 300% Strain	572	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1040	psi	
Flow : Break	690	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	600	%	
Flow : Break	470	%	
Tear Strength ²			ASTM D624
Across Flow	175	lbf/in	
Flow	135	lbf/in	
Compression Set ³ (73°F, 22 hr)	16	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	45		
Shore A, 5 sec	43		

Monprene® CP-29043

Teknor Apex Company - Thermoplastic Elastomer

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	400 to 440	°F
Middle Temperature	400 to 440	°F
Front Temperature	400 to 440	°F
Nozzle Temperature	400 to 440	°F
Processing (Melt) Temp	400 to 440	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Injection Notes		
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).		
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 420	°F
Cylinder Zone 2 Temp.	380 to 420	°F
Cylinder Zone 3 Temp.	380 to 420	°F
Cylinder Zone 4 Temp.	380 to 420	°F
Cylinder Zone 5 Temp.	380 to 420	°F
Die Temperature	380 to 420	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		
Notes		
¹ Typical properties: these are not to be construed as specifications.		
² Die C, 20 in/min		
³ Type 1		