



Monprene® CP-33142 XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-33142 CLR is a clear, UV resistant thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-33142 CLR is a low hardness, low density grade that exhibits medium flow characteristics, suitable for injection molding and extrusion.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Light Stabilized • Low Density • Low Hardness • Low Specific Gravity	• Lubricated • Medium Flow • Slip • Sunlight Resistant	• UV Absorbing • Without Fillers
Uses	• Consumer Applications • Gaskets	• Handles • Toothbrush Handles	• Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	195	psi	
Flow : 100% Strain	220	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	321	psi	
Flow : 300% Strain	362	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1060	psi	
Flow : Break	1010	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	710	%	
Flow : Break	680	%	
Tear Strength ²			ASTM D624
Across Flow	145	lbf/in	
Flow	138	lbf/in	
Compression Set ³ (73°F, 22 hr)	17	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	44		
Shore A, 5 sec	42		

Monprene® CP-33142 XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	95 to 120	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1