



Monprene® CP-35124 X1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-35124 X1 is a general purpose clear thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-35124 X1 is a low hardness grade thats suitable for injection molding and extrusion.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Low Density • Low Hardness • Low Specific Gravity	• Lubricated • Medium Flow • Slip	• Without Fillers
Uses	• Consumer Applications • Gaskets • Handles	• Kitchenware • Sporting Goods • Toothbrush Handles	• Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.880		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Flow : 100% Strain ²	243	psi	
Across Flow : 100% Strain ³	72.0	psi	
Tensile Stress			ASTM D412
Flow : 300% Strain ²	292	psi	
Across Flow : 300% Strain ³	128	psi	
Tensile Strength			ASTM D412
Across Flow : Break ³	1080	psi	
Flow : Break ²	1160	psi	
Tensile Elongation			ASTM D412
Flow : Break ²	1500	%	
Across Flow : Break ³	800	%	
Tear Strength ³			ASTM D624
Across Flow	158	lbf/in	
Flow	160	lbf/in	
Compression Set ⁴ (73°F, 22 hr)	13	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	27		
Shore A, 5 sec, Injection Molded	24		

Monprene® CP-35124 X1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	95 to 120	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 20 in/min

³ Die C, 20 in/min

⁴ Type 1