



Monprene® IN-29343 XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene IN-29343 XRD1 is a general purpose thermoplastic elastomer, available in NAT, BLK, and colors designed for a variety of industrial applications, including seals and gaskets. Monprene IN-29343 XRD1 is a low density, medium hardness, RoHS compliant grade suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Colorability • Good Flexibility • Good Processability • Good Toughness	• Low Density • Low Specific Gravity • Lubricated • Medium Flow • Medium Hardness	• Resilient • Slip • Without Fillers
Uses	• Flexible Grips • Gaskets • General Purpose • Grommets • Handles	• Industrial Applications • Knobs • Luggage • O-rings • Overmolding	• Plugs • Rubber Replacement • Safety Equipment • Seals
RoHS Compliance	• RoHS Compliant		
Appearance	• Black • Colors Available	• Natural Color • Translucent	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.900		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	141	psi	ASTM D412
Tensile Strength ² (Break)	1920	psi	ASTM D412
Tensile Elongation ² (Break)	800	%	ASTM D412
Tear Strength ²	262	lbf/in	ASTM D624
Compression Set ³ (73°F, 22 hr)	15	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	43		
Shore A, 5 sec, Injection Molded	41		

Monprene® IN-29343 XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 400	°F
Middle Temperature	360 to 400	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	360 to 400	°F
Processing (Melt) Temp	360 to 400	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	340 to 380	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	340 to 380	°F
Cylinder Zone 4 Temp.	340 to 380	°F
Cylinder Zone 5 Temp.	340 to 380	°F
Die Temperature	340 to 380	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1