



Monprene® IN-12090

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene IN-12090 is a general purpose thermoplastic elastomer, available in NAT and BLK, designed for a variety of industrial applications, including seals and gaskets. Monprene IN-12090 is a low density, high hardness TPE that is suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Additive Free • Chemical Resistant • General Purpose • Good Adhesion • Good Color Stability	• Good Moldability • Good Processability • Good Tear Strength • High Hardness • High Tensile Strength	• Low Density • Low Flow • Low Specific Gravity • Without Fillers
Uses	• Gaskets • Handles • Industrial Applications	• O-rings • Plugs • Profiles	• Rubber Replacement • Seals • Tubing
RoHS Compliance	• RoHS Compliant		
Appearance	• Black • Colors Available	• Natural Color • Translucent	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	620	psi	
Flow : 100% Strain	775	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	803	psi	
Flow : 300% Strain	1010	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	3000	psi	
Flow : Break	1920	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	830	%	
Flow : Break	670	%	
Tear Strength ²			ASTM D624
Across Flow	362	lbf/in	
Flow	340	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	30	%	
158°F, 22 hr	63	%	

Monprene® IN-12090

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	91		
Shore A, 5 sec	90		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	149	°F	ASTM D1525

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	420 to 460	°F
Middle Temperature	420 to 460	°F
Front Temperature	420 to 460	°F
Nozzle Temperature	420 to 460	°F
Processing (Melt) Temp	420 to 460	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	400 to 440	°F
Cylinder Zone 2 Temp.	400 to 440	°F
Cylinder Zone 3 Temp.	400 to 440	°F
Cylinder Zone 4 Temp.	400 to 440	°F
Cylinder Zone 5 Temp.	400 to 440	°F
Die Temperature	400 to 440	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1