



Monprene® CP-38128 CLR XRD4 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene CP-38128 CLR XRD4 is a high performance thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-38128 CLR XRD4 is a low hardness, low density, clear grade that is suitable for both injection molding and extrusion.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Chemical Resistant • Good Adhesion • Good Colorability • Good Moldability	• Good Processability • Good Processability • Low Density • Low Hardness • Low Specific Gravity	• Lubricated • Medium Flow • Slip • Without Fillers
Uses	• Consumer Applications • Gaskets • Handles	• Knobs • Rubber Replacement • Sporting Goods	• Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.892		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	30	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	856	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	32		
Shore A, 5 sec, Injection Molded	30		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	340 to 380	°F
Front Temperature	340 to 380	°F
Nozzle Temperature	340 to 380	°F

Monprene® CP-38128 CLR XRD4 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Processing (Melt) Temp	340 to 380	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	320 to 360	°F
Cylinder Zone 2 Temp.	320 to 360	°F
Cylinder Zone 3 Temp.	320 to 360	°F
Cylinder Zone 4 Temp.	320 to 360	°F
Cylinder Zone 5 Temp.	320 to 360	°F
Die Temperature	320 to 360	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.