



Monprene® MP-2103

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene MP-2103 is a general purpose thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene MP-2103 is a medium density, high hardness, RoHS compliant grade suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • General Purpose • Good Colorability • Good Melt Strength	• Good Mold Release • Good Moldability • Good Processability • Good Processing Stability • Halogen Free	• High Hardness • Medium Density • Medium Flow • Slip
Uses	• Caps • Consumer Applications • General Purpose	• Grommets • Handles • Knobs	• Profiles
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	760	psi	
Flow : 100% Strain	984	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	893	psi	
Flow : 300% Strain	1160	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	2190	psi	
Flow : Break	1900	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	740	%	
Flow : Break	590	%	
Tear Strength ²			ASTM D624
Across Flow	261	lbf/in	
Flow	312	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	52	%	
158°F, 22 hr	75	%	

Monprene® MP-2103

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 1 sec, Injection Molded	32		
Shore D, 5 sec, Injection Molded	30		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 4 Temp.	390 to 480	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1