



Monprene® OM-10160-01

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene OM-10160-01 is a specialty thermoplastic elastomer, available in NAT, BLK, and colors, designed for overmolding applications like grips and anti-skid parts for a variety of consumer and industrial products. Monprene OM-10160-01 is a medium hardness, low density opaque grade that exhibits excellent adhesion to nylon.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Adhesion	• Good Processability • Low Density	• Low Specific Gravity • Medium Hardness
Uses	• Appliances • Bonding • Cell Phones • Flexible Grips	• Handles • Knobs • Overmolding • Power/Other Tools	• Sporting Goods • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Colors Available	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.930		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	1100	psi	ASTM D412
Tensile Strength (Break)	1150	psi	ASTM D412
Tensile Elongation (Break)	300	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Additional Information	Nominal Value	Unit	
Adhesion to Nylon			

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	150	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	450 to 470	°F
Middle Temperature	480 to 510	°F
Front Temperature	510 to 530	°F

Monprene® OM-10160-01
Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Nozzle Temperature	520 to 550	°F
Processing (Melt) Temp	515 to 530	°F
Mold Temperature	75 to 140	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 120	rpm
Cushion	0.150 to 1.00	in

Notes

¹ Typical properties: these are not to be construed as specifications.