



# Monprene® OM-19140 NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

Monprene OM-19140 is part of a series of adhesion-modified thermoplastic elastomers (available from 40 to 70 Shore A) designed for over-molding (insert and multi-shot) and co-extrusion onto polyamide (Nylon), including: PA 6, PA66, PA12, etc. These materials exhibit dry haptics and low compression set are well suited for overmolded seals or grips. Monprene OM-19140 is REACH-SVHC and RoHS compliant and offers several benefits including superior adhesion onto polystyrene and easy molding with a wide processing window.

### General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Chemical Resistant • Conformable • Ductile • Filled • Good Colorability	• Good Compression Set • Good Flexibility • Good Flow • Good Impact Resistance • Good Moldability • Halogen Free	• High Elasticity • Low Compression Set • Lubricated • Medium Density • Medium Hardness • Soft
Uses	• Bonding • Consumer Applications	• Industrial Applications • Overmolding	• Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.08		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (50% Strain)	105	psi	ASTM D412
Tensile Stress <sup>3</sup> (100% Strain)	160	psi	ASTM D412
Tensile Strength <sup>3</sup> (Break)	440	psi	ASTM D412
Tensile Elongation <sup>3</sup> (Break)	390	%	ASTM D412
Tear Strength <sup>3</sup>	90.0	lbf/in	ASTM D624
Compression Set			ASTM D395B
70°F, 22 hr	10	%	
158°F, 22 hr	37	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	40		
Shore A, 5 sec, Injection Molded	38		
Additional Information	Nominal Value	Unit	
Adhesion to Nylon			
Adhesion to PA6			
Adhesion to PA66			

# Monprene® OM-19140 NAT (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	450 to 470	°F
Middle Temperature	470 to 490	°F
Front Temperature	490 to 510	°F
Nozzle Temperature	490 to 510	°F
Processing (Melt) Temp	470 to 520	°F
Mold Temperature	90 to 130	°F
Injection Pressure	5000 to 6000	psi
Injection Rate	Fast	
Holding Pressure	2800 to 3000	psi

### Injection Notes

Drying is recommended to achieve a moisture level  $\leq 0.08\%$ . Dry the pellets for 2 to 4 hours at 185°F (85°C).

For overmolding to Nylon 6,6, use higher temperature settings than the recommended processing condition.

Nylon substrate must not be exposed to open air for long, to avoid moisture adsorption.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 20 in/min

<sup>3</sup> Die C, 20 in/min