



# Monprene® OM-19340 NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

Monprene OM-19340 NAT is part of a series of adhesion-modified thermoplastic elastomers (available from 30 to 70 Shore A) designed for over-molding (insert and multi-shot) and co-extrusion onto polystyrene, including general-purpose PS (GPPS), high-impact PS (HIPS), and their blends. These materials exhibit dry haptics and are well suited for grips and other soft-touch parts. Monprene OM-19340 NAT is REACH-SVHC and RoHS compliant and offers several benefits including superior adhesion onto polystyrene and easy molding with a wide processing window.

### General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • BPA Free • Chemical Resistant • Conformable • Ductile • Excellent Processability	• Filled • Good Colorability • Good Flexibility • Good Flow • Good Impact Resistance • Good Moldability	• Halogen Free • High Elasticity • Low Hardness • Medium Density • Soft
Uses	• Bonding • Consumer Applications • Flexible Grips	• Household Goods • Housings • Industrial Applications	• Overmolding • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

## ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (100% Strain)	115	psi	ASTM D412
Tensile Stress <sup>2</sup> (300% Strain)	215	psi	ASTM D412
Tensile Strength <sup>2</sup> (Break)	1000	psi	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	680	%	ASTM D412
Tear Strength <sup>2</sup>	110	lbf/in	ASTM D624
Compression Set <sup>3</sup> (73°F, 22 hr)	23	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	43		
Shore A, 5 sec, Injection Molded	40		
Additional Information	Nominal Value	Unit	
Adhesion to HIPS			
Adhesion to PS			

# Monprene® OM-19340 NAT (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	320 to 350	°F
Middle Temperature	340 to 370	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

### Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

For any overmolding process it is recommended that the process temperatures for the TPE material be set at least 50°F (10°C) higher than the melt temperature of the substrate material.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C, 20 in/min

<sup>3</sup> Type 1