



Monprene® OM-12265-01 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene OM-12265-01 is a specialty thermoplastic elastomer designed for overmolding applications like grips and anti-skid parts for consumer and industrial products. Monprene OM-12265-01 is a medium hardness, low density, UV stabilized grade that exhibits excellent adhesion to PC, ABS, and PC/ABS.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Good Adhesion • Good Moldability • Light Stabilized	• Low Density • Low Specific Gravity • Lubricated • Medium Flow	• Medium Hardness • Slip • UV Resistant
Uses	• Appliances • Bonding • Cell Phones • Flexible Grips	• Handles • Knobs • Overmolding • Power/Other Tools	• Rubber Replacement • Sporting Goods • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color	• Translucent	
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.960		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	900	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	68		
Shore A, 5 sec, Injection Molded	66		
Additional Information	Nominal Value	Unit	
Adhesion to ABS			
Adhesion to PC			
Adhesion to PC/ABS			

Monprene® OM-12265-01 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	140	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	370 to 420	°F
Middle Temperature	370 to 420	°F
Front Temperature	370 to 420	°F
Nozzle Temperature	370 to 420	°F
Processing (Melt) Temp	370 to 420	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Moisture can degrade the material. Drying is suggested. This can be accomplished by placing the material in a desiccant dryer for 2 to 4 hours at 140°F.

Notes

¹ Typical properties: these are not to be construed as specifications.