



Monprene® OM-17460 NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene OM-17460 NAT is designed for overmolding applications for consumer products. Monprene OM-17460 NAT is a natural grade that exhibits excellent adhesion to PC. This grade is suitable for both injection molding and extrusion.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Light Stabilized	• Medium Density • Medium Flow	• Medium Hardness
Uses	• Appliances • Bonding • Cell Phones • Flexible Grips	• Handles • Knobs • Overmolding • Power/Other Tools	• Sporting Goods • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	50	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	580	psi	ASTM D412
Tensile Elongation (Break)	400	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	62		
Shore A, 5 sec, Injection Molded	60		
Additional Information	Nominal Value	Unit	
Adhesion to PC			
Adhesion to PC/ABS			

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	140	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	420 to 470	°F
Middle Temperature	420 to 470	°F

Monprene® OM-17460 NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Front Temperature	420 to 470	°F
Nozzle Temperature	420 to 470	°F
Processing (Melt) Temp	420 to 470	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Moisture can degrade the material. Drying is suggested. This can be accomplished by placing the material in a desiccant dryer for 2 to 4 hours at 140°F.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	400 to 450	°F
Cylinder Zone 2 Temp.	400 to 450	°F
Cylinder Zone 3 Temp.	400 to 450	°F
Cylinder Zone 4 Temp.	320 to 360	°F
Cylinder Zone 5 Temp.	400 to 450	°F
Die Temperature	400 to 450	°F

Notes

¹ Typical properties: these are not to be construed as specifications.