



# Monprene® OM-19460 NAT (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

Monprene OM-19460 NAT is part of a series of adhesion-modified thermoplastic elastomers (available from 40 to 70 Shore A) designed for over-molding (insert and multi-shot) and co-extrusion onto many engineering thermoplastics, including: PC, ABS, PC/ABS, CoPE, PET, PBT, PMMA, PSA, ASA, SAN, POM, and more. These materials exhibit dry haptics and are well suited for grips and other soft-touch parts. Monprene OM-19460 NAT has a medium density and offers several benefits including superior adhesion onto polystyrene and easy molding with a wide processing window.

### General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Chemical Resistant • Conformable • Crack Resistant • Good Colorability	• Good Flexibility • Good Flow • Good Impact Resistance • Good Moldability • Good Scratch Resistance	• Good Toughness • Halogen Free • Low Compression Set • Medium Density • Medium Hardness
Uses	• Bonding • Consumer Applications • Gaskets • Industrial Applications	• Industrial Parts • Knobs • Lids • Overmolding	• Pipe Seals • Safety Equipment • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

## ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.15		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (100% Strain)	270	psi	ASTM D412
Tensile Strength <sup>2</sup> (Break)	550	psi	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	600	%	ASTM D412
Tear Strength <sup>2</sup>	140	lbf/in	ASTM D624
Compression Set <sup>3</sup> (73°F, 22 hr)	27	%	ASTM D395
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	62		
Shore A, 5 sec, Injection Molded	60		
Additional Information	Nominal Value	Unit	
Adhesion to ABS			
Adhesion to COPE			
Adhesion to PBT			
Adhesion to PC			
Adhesion to PC/ABS			
Adhesion to PMMA			
Adhesion to POM			

# Monprene® OM-19460 NAT (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	392 to 464	°F
Middle Temperature	392 to 482	°F
Front Temperature	428 to 500	°F
Nozzle Temperature	428 to 500	°F
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	90 to 130	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

### Injection Notes

Drying is strongly suggested to enhance bondability.

For any overmolding process it is recommended that the process temperatures for the TPE material be set at least 50°F (10°C) higher than the melt temperature of the substrate material.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C, 20 in/min

<sup>3</sup> Type 1