



# Monprene® R2 PC-12151 NAT XRD4 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

The Monprene® RX PC-15100 series of thermoplastic elastomers (TPEs) is formulated to contain post-consumer recycled (PCR) content, reducing dependency on virgin petroleum-based plastic and contributing towards a circular economy. These high-flow materials, designed for injection molding or overmolding onto polypropylene, perform and process like prime TPE, and are available in a light, natural color. Monprene R2 PC-12151 NAT XRD4 is a 45 Shore A TPE containing 25% PCR content.

### General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Recycled Content	• Post-Consumer (PCR), 25%		
Features	• Chemical Resistant	• Good Processability	• High Tensile Strength
	• Good Adhesion	• Good Toughness	• Low Compression Set
	• Good Colorability	• Halogen Free	• Low Density
	• Good Flexibility	• High Elongation	• Medium Hardness
	• Good Moldability	• High Flow	• Resilient
Uses	• Consumer Applications	• Knobs	• Soft Touch Applications
	• Flexible Grips	• Luggage	• Sporting Goods
	• General Purpose	• Overmolding	• Toothbrush Handles
	• Handles	• Rubber Replacement	• Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.862		ASTM D792
Melt Mass-Flow Rate (MFR) (150°C/2.16 kg)	> 50	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Break)	218	psi	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	200	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec, Injection Molded)	45		ASTM D2240

## Processing Information

Injection	Nominal Value	Unit
Rear Temperature	311 to 374	°F
Middle Temperature	320 to 392	°F
Front Temperature	320 to 410	°F
Nozzle Temperature	320 to 410	°F
Processing (Melt) Temp	320 to 410	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Moderate-Fast	

### Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C, 20 in/min