



Monprene® R6 CP-10165 BLK

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

The Monprene RX CP-10100 Series of thermoplastic elastomer compounds is formulated to contain post-consumer (PCR) content, reducing dependency on virgin petroleum-based plastic and contributing towards a circular economy. These materials are designed specifically for consumer product applications requiring a soft, rubber-like feel. Monprene R6 CP-10165 BLK is a medium hardness, low density, unfilled grade that is suitable for injection molding and contains minimum 60% PCR content.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Recycled Content	• Post-Consumer (PCR), 60%		
Features	• Chemical Resistant • General Purpose • Good Adhesion	• Good Flexibility • Good Processability • Low Density	• Low Hardness • Low Specific Gravity
Uses	• Appliances • Consumer Applications • Flexible Grips • Furniture • Handles	• Household Goods • Knobs • Personal Care • Rubber Replacement • Safety Equipment	• Soft Touch Applications • Stationary Supplies • Toys • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.892		ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	75	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
Across Flow : 100% Strain	218	psi	
Flow : 100% Strain	348	psi	
Tensile Stress			ISO 37
Across Flow : Break	1250	psi	
Flow : Break	711	psi	
Tensile Elongation			ISO 37
Across Flow : Break	830	%	
Flow : Break	570	%	
Compression Set			ISO 815
73°F, 70 hr	25	%	
158°F, 24 hr	49	%	
212°F, 24 hr	65	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	65		ISO 868

Monprene® R6 CP-10165 BLK

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	320 to 356	°F
Middle Temperature	338 to 392	°F
Front Temperature	374 to 410	°F
Nozzle Temperature	374 to 428	°F
Processing (Melt) Temp	374 to 428	°F
Mold Temperature	68 to 122	°F
Injection Rate	Moderate-Fast	

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 65 °C (150 °F).

Notes

¹ Typical properties: these are not to be construed as specifications.