



Monprene® SP-13064

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene SP-13064 is a high performance thermoplastic elastomer that is designed for a variety of consumer applications. Monprene SP-13064 is a translucent, medium hardness, low density, high flow grade. This grade is suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Colorability • Good Mold Release • Good Moldability	• Good Processability • Low Density • Low Specific Gravity	• Medium Flow • Medium Hardness • Without Fillers
Uses	• Consumer Applications • Gaskets • Handles	• Kitchenware • Sporting Goods • Tubing	• Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	10	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	361	psi	
Flow : 100% Strain	511	psi	
Tensile Stress ²			ASTM D412
300% Strain	650	psi	
Flow : 300% Strain	809	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1840	psi	
Flow : Break	1450	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	590	%	
Flow : Break	570	%	
Tear Strength ²			ASTM D624
Across Flow	300	lbf/in	
Flow	254	lbf/in	
Compression Set ³ (73°F, 22 hr)	15	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	66		
Shore A, 5 sec, Injection Molded	64		

Monprene® SP-13064

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	50 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 4 Temp.	390 to 480	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1