



Monprene® RG-63458 NAT XRD1 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

General

Material Status	• Preliminary Data		
Availability	• North America		
Uses	<ul style="list-style-type: none"> • Closures • Consumer Applications • Gaskets • Handles 	<ul style="list-style-type: none"> • Kitchenware • Medical/Healthcare Applications • Packaging • Safety Equipment 	<ul style="list-style-type: none"> • Sporting Goods • Toothbrush Handles • Tubing • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.970		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Flow (300% Strain)	410	psi	ASTM D412
Tensile Strength - Flow (Break)	1670	psi	ASTM D412
Tensile Elongation - Flow (Break)	780	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness ²			ASTM D2240
Shore A, 1 sec	60		
Shore A, 5 sec	58		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Aged for 24 hr