



Monprene® SP-19947

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene SP-19947 is a high performance thermoplastic elastomer designed for a variety of consumer product applications including sporting goods. Monprene SP-19947 is a low hardness, low density medium flow UV stabilized grade that is designed for injection molding but can be extruded.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • General Purpose • Good Adhesion • Good Colorability • Good Flexibility • Good Moldability	• Good Processability • Good Toughness • Low Density • Low Hardness • Low Specific Gravity • Lubricated	• Medium Flow • Resilient • Slip • Sunlight Resistant • UV Resistant • Without Fillers
Uses	• Consumer Applications • Flexible Grips • General Purpose	• Overmolding • Rubber Replacement • Soft Touch Applications	• Sporting Goods
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	189	psi	
Flow : 100% Strain	268	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	284	psi	
Flow : 300% Strain	358	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	978	psi	
Flow : Break	469	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	790	%	
Flow : Break	540	%	
Tear Strength ²			ASTM D624
Across Flow	139	lbf/in	
Flow	115	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	20	%	
158°F, 22 hr	48	%	

Monprene® SP-19947

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	50		
Shore A, 5 sec, Injection Molded	47		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 450	°F
Middle Temperature	370 to 460	°F
Front Temperature	380 to 470	°F
Nozzle Temperature	390 to 480	°F
Processing (Melt) Temp	390 to 480	°F
Mold Temperature	95 to 120	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 450	°F
Cylinder Zone 2 Temp.	370 to 460	°F
Cylinder Zone 3 Temp.	380 to 470	°F
Cylinder Zone 4 Temp.	380 to 470	°F
Cylinder Zone 5 Temp.	390 to 480	°F
Die Temperature	390 to 480	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1