



Sarlink® TPE ME-2540 XRD3 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

The Sarlink ME-2500 Series are super high flow, high density, high performance thermoplastic elastomers designed for demanding exterior automotive molding applications, including window encapsulation. Sarlink ME-2540 XRD3 is a medium hardness, high density, RoHS compliant grade suitable for injection molding.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Flexibility	• Good Processability • Good Surface Finish • Good Toughness • High Density	• High Flow • High Specific Gravity • Medium Hardness • UV Resistant
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Window Encapsulation • Rubber Replacement	
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.15		ISO 1183
Melt Mass-Flow Rate (MFR) (170°C/2.16 kg)	61	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	187	psi	ASTM D412
Tensile Stress (Break)	383	psi	ASTM D412
Tensile Elongation (Break)	590	%	ASTM D412
Tear Strength ²	80.0	lbf/in	ASTM D624
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 868
Shore A, 1 sec	41		
Shore A, 5 sec	38		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	48.0	Pa·s	ASTM D3835
Additional Information			
Adhesion to glass with primer			

Sarlink® TPE ME-2540 XRD3 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	338 to 374	°F
Middle Temperature	347 to 383	°F
Front Temperature	356 to 401	°F
Nozzle Temperature	356 to 401	°F
Processing (Melt) Temp	356 to 401	°F
Mold Temperature	59 to 104	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 176°F (80°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C